

PPG SIGMADUR™ 550

DESCRIPTION

Two-component, aliphatic acrylic polyurethane finish

PRINCIPAL CHARACTERISTICS

- Unlimited recoatable
- Excellent resistance to atmospheric exposure conditions
- Good color and gloss retention
- Cures at temperatures down to -5°C (23°F)
- Resistant to splash of mineral and vegetable oils, paraffins, aliphatic petroleum products and mild chemicals
- Can be recoated even after long atmospheric exposure
- Good application properties

COLOR AND GLOSS LEVEL

- White and various other colors (see also SIGMACARE shade card)
- Gloss

Note:

- Certain colors, especially red, orange, and yellow may require additional coats for adequate hiding, especially if applied over primers with a significant color contrast

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.3 kg/l (10.8 lb/US gal)
Volume solids	55 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 334.0 g/kg EUR Directive: 2004/42/IIA(i)(500) 459 g/l max. 430.0 g/l (approx. 3.6 lb/US gal)
Recommended dry film thickness	50 - 75 µm (2.0 - 3.0 mils) depending on system
Theoretical spreading rate	11.0 m²/l for 50 µm (441 ft²/US gal for 2.0 mils)
Dry to touch	1 hour
Overcoating Interval	Minimum: 6 hours Maximum: Unlimited
Full cure after	4 days
Shelf life	Base: at least 36 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

PPG SIGMADUR™ 550

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Previous coat (epoxy or polyurethane) must be dry and free from any contamination
 - Previous coat: surface should be sufficiently roughened if necessary
-

Substrate temperature and application conditions

- Substrate temperature during application at -5°C (23°F) is acceptable; provided the substrate is free from ice and dry
 - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
 - Relative humidity during application and curing should not exceed 85%
 - Should condensation on the surface occur during, or soon after application, this could result in color and gloss change
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 88:12 (7.33:1)

- The temperature of the mixed base and hardener should be above 10°C (50°F), otherwise extra thinner may be required to obtain application viscosity
 - Thinner should be added after mixing the components
 - Adding too much thinner results in reduced sag resistance
-

Pot life

5 hours at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life
-

Air spray

Recommended thinner

THINNER 21-06

Volume of thinner

3 - 5%, depending on required thickness and application conditions

Nozzle orifice

1.0 - 1.5 mm (approx. 0.040 - 0.060 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

PPG SIGMADUR™ 550

Airless spray**Recommended thinner**

THINNER 21-06

Volume of thinner

3 - 5%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.43 – 0.48 mm (0.017 – 0.019 in)

Nozzle pressure

20.0 MPa (approx. 200 bar; 2901 p.s.i.)

Brush/roller**Recommended thinner**

THINNER 21-06

Volume of thinner

0 – 5%

Cleaning solvent

- THINNER 90-53

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
50 µm (2.0 mils)	11.0 m ² /l (441 ft ² /US gal)
60 µm (2.4 mils)	9.2 m ² /l (368 ft ² /US gal)
75 µm (3.0 mils)	7.3 m ² /l (294 ft ² /US gal)

PPG SIGMADUR™ 550

Overcoating interval for DFT up to 50 µm (2.0 mils)

Overcoating with...	Interval	-5°C (23°F)	0°C (32°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	24 hours	16 hours	8 hours	6 hours	5 hours	3 hours
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited	Unlimited	Unlimited

Note:

- Surface should be dry and free from any contamination

Curing time for DFT up to 60 µm (2.4 mils)

Substrate temperature	Dry to handle	Full cure
-5°C (23°F)	24 hours	15 days
0°C (32°F)	16 hours	11 days
10°C (50°F)	8 hours	6 days
20°C (68°F)	6 hours	4 days
30°C (86°F)	5 hours	3 days
40°C (104°F)	3 hours	48 hours

Notes:

- Adequate ventilation must be maintained during application and curing
- Premature exposure to early condensation and rain may cause color and gloss change

Pot life (at application viscosity)

Mixed product temperature	Pot life
10°C (50°F)	7 hours
20°C (68°F)	5 hours
30°C (86°F)	3 hours
40°C (104°F)	2 hours

SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes
- Contains a polyisocyanate curing agent

PPG SIGMADUR™ 550

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Guide | PPG SIGMACARE PLUS | Online guide to maintenance at sea
- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

