

PPG SIGMAGUARD™ CSF 650

DESCRIPTION

Two-component, solvent-free, amine-cured epoxy coating

PRINCIPAL CHARACTERISTICS

- Tank coating for crude oil/ballast and aliphatic petroleum products
- Also suitable as a coating system for the storage and transportation of drinking water
- Good resistance to various chemicals
- Excellent resistance to crude oil up to 60°C (140°F)
- Meets the requirements of EI 1541 2.2 (coating systems for aviation fuel storage tanks and pipes)
- One-coat protection for steel structures, ships and storage tanks with excellent corrosion resistance
- Can be applied by heavy-duty, single-feed, airless spray equipment (60:1)
- Reduced explosion risk and fire hazard
- Good visibility due to light color
- A clear (semi-transparent) version is available for systems reinforced with chopped glass fibers or glass fiber mats

COLOR AND GLOSS LEVEL

- Green, offwhite, clear (semi-transparent)
- Gloss

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.3 kg/l (10.8 lb/US gal)
Volume solids	100%
VOC (Supplied)	max. 143.0 g/l (approx. 1.2 lb/US gal) Directive 2010/75/EU, SED: max. 109.0 g/kg EPA Method 24: 120.0 g/ltr (1.0 lb/USgal)
Recommended dry film thickness	300 - 600 µm (12.0 - 24.0 mils) depending on system
Theoretical spreading rate	3.3 m ² /l for 300 µm (134 ft ² /US gal for 12.0 mils)
Dry to touch	8 hours
Overcoating Interval	Minimum: 24 hours Maximum: 20 days
Full cure after	5 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

PPG SIGMAGUARD™ CSF 650

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to ISO-Sa2½, blasting profile 50 – 100 µm (2.0 – 4.0 mils)
- Suitable primer; NOVAGUARD 260, SIGMACOVER 280, SIGMAPRIME series or SIGMACOVER 522, depending on system requirements
- Steel; power tooling to ISO-St3 for small and isolated areas (like repairs and joint welds) in fresh water and potable water tanks where spot blasting might be impractical

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application should be at least 3°C (5°F) above dew point

SYSTEM SPECIFICATION

- SIGMAGUARD CSF 650: 1 x 300 µm (12.0 mils); or a suitable primer of 50 µm (2.0 mils) + SIGMAGUARD CSF 650: 1 x 250 µm (10.0 mils)

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 4:1

- At lower temperature, the viscosity will be too high for spray application
- For recommended application instructions, see working procedure
- The temperature of the mixed base and hardener should preferably be above 20°C (68°F)
- No thinner should be added

Induction time

0 minute

Note:

- No induction time required

Pot life

1 hour at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life

PPG SIGMAGUARD™ CSF 650

Airless spray

- Use heavy-duty, single-feed, airless spray equipment, preferably 60:1 pump ratio and suitable high-pressure hoses/ in-line heating or insulated hoses may be necessary to avoid cooling down of paint in hoses at low air temperature
- Application with 45:1 airless spray equipment is possible, provided in-line, heated high-pressure hoses are used
- Length of hoses should be as short as possible

Recommended thinner

No thinner should be added

Nozzle orifice

Approx. 0.64 mm (0.025 in)

Nozzle pressure

At 20°C (68°F) paint temperature min. 28.0 MPa (approx. 280 bar; 4061 p.s.i.). At 30°C (86°F) min. 22.0 MPa (approx. 220 bar; 3191 p.s.i.)

Note:

- In case of using 45:1 airless spray equipment, the paint must be heated to approximately 30°C (86°F) in order to obtain the right application viscosity

Brush/roller

Recommended thinner

For stripe coating and spot repair only, no thinner should be added

Cleaning solvent

- THINNER 90-53 or THINNER 90-83
 - All application equipment must be cleaned immediately after use
 - Paint inside the spraying equipment must be removed before the pot life has been expired
-

PPG SIGMAGUARD™ CSF 650

ADDITIONAL DATA

Measuring wet film thickness

- A difference is often obtained between the measured apparent WFT and the real applied WFT. This is due to the thixotropy and the surface tension of the paint, which retards the release of air, trapped in the paint film for some time.
- A practical recommendation is to apply a WFT, which is equal to the specified DFT plus 60 µm (2.4 mils)

Measuring dry film thickness

- Penetration of the measuring gauge into the paint film may be observed due to low initial hardness. Care should be taken to prevent unnecessary low readings.
- The DFT should be measured using a calibration foil of known thickness placed in between the coating and the measuring device

Washing procedures

- The recommended washing procedure must be applied after completion of the application
- Sufficient time for full-curing and ventilation must be allowed in accordance with the recommendations as stated in the latest Product Data Sheets and working procedure.
- Always an adequate washing procedure should be followed
- Several adequate washing procedures are available and may be used (see e.g. washing procedure described in relevant certificate)

Example 1: Adequate washing procedure

- After full curing of the system as per the latest PDS, the tank should be filled completely with fresh tap water
- The fresh tap water should remain in the tanks at least 4 full days
- Afterwards all tank compartments such as inner hull sides, bottom and deckheads etc. should be thoroughly washed using high pressure water
- After washing, the tanks should be thoroughly drained
- After this procedure the tanks will be fit to carry drinking water

Example 2: Adequate washing procedure

- All personnel should wear watertight suits, boots and gloves properly cleaned with a sodium hypochlorite solution (1% active chlorine per liter)
- All tank sides, bottom and deckheads etc. should be brush cleaned or high-pressure spray cleaned with 1% active chlorine solution as above. This can also be done by butterworth washing.
- All parts should be high pressure cleaned with tap water and tanks drained
- Concentrated active chlorine solution should be sprinkled on bottom; approx. 1 liter per 10 m² (1 quart per 100 ft²)
- Tanks should be filled with tap water to a depth of approx. 20 cm (8 inches) and the water should remain in the tank for at least 2 hours (max. 24 hours)
- Tanks should be thoroughly flushed out with tap water
- Depending upon local regulations it may be necessary to take water samples, after filling tank completely, to check on bacteria
- After this procedure the tanks will be fit to carry drinking water

PPG SIGMAGUARD™ CSF 650

Spreading rate and film thickness

DFT	Theoretical spreading rate
250 µm (10.0 mils)	4.0 m ² /l (160 ft ² /US gal)
300 µm (12.0 mils)	3.3 m ² /l (134 ft ² /US gal)
600 µm (24.0 mils)	1.7 m ² /l (67 ft ² /US gal)

Note:

- Maximum DFT when brushing: 200 µm (8.0 mils)

Overcoating interval for DFT up to 300 µm (12.0 mils)

Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	3.5 days	36 hours	24 hours	16 hours	12 hours
	Maximum	20 days	20 days	20 days	14 days	7 days

Note:

- Surface should be dry and free from any contamination

Curing time for DFT up to 300 µm (12.0 mils)

Substrate temperature	Dry to handle	Full cure
5°C (41°F)	60 hours	15 days
10°C (50°F)	30 hours	7 days
20°C (68°F)	16 hours	5 days
30°C (86°F)	10 hours	3 days
40°C (104°F)	8 hours	48 hours

Notes:

- Adequate ventilation must be maintained during application and curing
- For drinking water tanks, a tank wash should be carried out after full cure and before the tank goes into service
- When used as coating system for storage and transport of drinking water the recommended working and washing procedure should be followed

PPG SIGMAGUARD™ CSF 650

Pot life (at application viscosity)	
Mixed product temperature	Pot life
20°C (68°F)	1 hour
30°C (86°F)	45 minutes
40°C (104°F)	25 minutes

Note:

- Due to exothermic reaction, temperature during and after mixing may increase

DISCLAIMER

- SIGMAGUARD CSF 650 is approved for purpose in accordance with the requirements of the relevant certificate
- PPG Protective & Marine Coatings does not accept any responsibility or liability for any odor, taste or contamination imparted to the drinking water from the coatings or products retained in the coating

SAFETY PRECAUTIONS

- Ventilation should be provided in confined spaces to maintain good visibility
- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes
- If workers are exposed to concentrations above the exposure limit, they must use appropriate personal protective equipment (PPE)
- See Safety Data Sheet and product label for complete safety and precaution requirements

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Guide | Tank maintenance | Our guide to the economical repair of corroded tank bottoms
- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

PPG SIGMAGUARD™ CSF 650

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

