

PRODUCT CODE 0064

Apcolite Premium Satin Enamel

Asian Paints Apcolite Satin Enamel is a soft sheen enamel with the gentle, soothing sheen of a Satin fabric. It is just as durable as premium high gloss enamels and gives a long lasting washable finish.

PRODUCT BENEFITS

Soft Sheen Finish

Apcolite Premium Satin Enamel gives you a rich, sophisticated look that makes your house look a cut above the rest.

Stain Guard

Superior washability & stain resistance helps you remove stains easily.

Warranty

Apcolite Premium Satin Enamel comes with 2 years* of Film integrity warranty.

Anti-fungal Shield

The imported biopack in Apcolite Premium Satin Enamel protects surfaces from black spots and retains the beauty of your house!

High Coverage

Apcolite Premium Satin Enamel covers upto 25% more area than regular enamels – which means more savings for you!



SOLVENT BASED

asianpaints


LEAD FREE* GUARANTEE

* All Asian Paints products contain no added Lead, Mercury, Arsenic or Chromium from April 2008.



PRODUCT FEATURES

WASHABILITY




✓ **BEST IN CLASS**

HIGH

MEDIUM

LOW


AVAILABLE PACKS



Shelf life: 5 years from date of manufacture in original tightly closed containers away from direct sunlight and excessive heat.

COLOURS AVAILABLE

1788*



*Currently available in 1788 shades as per the Colourworld Fandek

FINISH

MATT **LOW SHEEN** HIGH SHEEN HIGH GLOSS

✓ **SILKY SMOOTH**

Refer to sheen levels in technical details

COVERAGE

On smooth masonry surface by brushing



1 COAT

240 - 280
sq.ft./ltr**



2 COATS

110 - 130
sq.ft./ltr**


**Actual coverage may vary from the quoted coverage due to factors such as method and condition of application and surface roughness and porosity.

HOW TO APPLY

PRE PAINTING STEPS




PLASTER New masonry surfaces must be allowed to cure completely. It is recommended to allow 28 days as the curing time for new masonry surfaces.



CLEANING Surface should be free from any loose paint, dust or grease. Growths of fungus, algae or moss should be removed by wire brushing and water. In case of areas having excessive dampness use Asian Paints DampBlock to limit further dampness. When the underlying surface exhibits chalkiness, in spite of thorough surface cleaning, use Asian Paints SmartCare Exterior Sealer.



FILLING FOR CRACKS For filling masonry upto 3mm use Asian Paints SmartCare Crack Seal.



FILLING FOR HOLES & DENTS

In case of dents and holes use Asian Paints Acrylic Wall Putty or white cement and fine sand in the ratio 1:3

Apcolite Premium Satin Enamel should not be applied on surfaces / substrates that are subjected to continuous seepage or dampness.

PAINT APPLICATION PROCESS

APPLICATION	CODE	THINNER	DILUTION %	APPLICATION VISCOSITY ¹	RECOATING PERIOD
STEP 1 SANDING					
SAND THE SURFACE WITH SAND PAPER 180 AND WIPE CLEAN					
STEP 2 METAL PRIMER (METAL) / DECOPRIME ST (MASONRY) / WOOD PRIMER (WOOD)	0005 0359 0007	MTO*	BRUSH 4 - 10 SPRAY 12 - 15	BRUSH 30 - 40 SPRAY 20 - 25	6 - 8 HRS
STEP 3 KNIFING PASTE FILLER (METAL / WOOD) WALL PUTTY (MASONRY) PUTTY KNIFE	0016 1354	WATER OR MTO	BASED ON REQUIREMENT	BASED ON REQUIREMENT	6 - 8 HRS 4 - 6 HRS
STEP 4 SANDING					
SAND THE SURFACE WITH SAND PAPER 180 AND WIPE CLEAN					
STEP 5 METAL PRIMER (METAL) / DECOPRIME ST (MASONRY) / WOOD PRIMER (WOOD)	0005 0359 0007	MTO*	BRUSH 4 - 10 SPRAY 12 - 15	BRUSH 30 - 40 SPRAY 20 - 25	6 - 8 HRS
STEP 6 SANDING					
SAND THE SURFACE WITH SAND PAPER 320 AND WIPE CLEAN					
STEP 7 FIRST COAT APCOLITE SATIN ENAMEL BRUSH / SPRAY / ROLLER	0064	MTO*	BRUSH 8 - 10 SPRAY 12 - 15	BRUSH 35 - 40 SPRAY 22 - 25	6 - 8 HRS
STEP 8 SECOND COAT APCOLITE SATIN ENAMEL BRUSH / SPRAY / ROLLER	0064	MTO*	BRUSH 8 - 10 SPRAY 12 - 15	BRUSH 35 - 40 SPRAY 22 - 25	6 - 8 HRS

1. As measured through a Ford cup.

2. Recoat period is quoted for 25°C and 50% Relative Humidity, these may vary under different conditions.

* Mineral Turpentine Oil

3. Ensure that the metal substrates are free from oil, grease and rust before paint application.

*Use 2 coats of Trucare Yellow metal PU primer as undercoat for 2 years of Film integrity warranty.

HOW TO CHOOSE COLOURS

Browse through Asian Paints colour tools to help you find the right colour combination

COLOUR SPECTRA FAN DECK*

APCOLITE ENAMEL SHADE CARD



*These shades are for reference only. Please refer to the Colour Spectra or Colour Palette for correct shade reference

ADDITIONAL INFORMATION

POST PAINTING CARE

For the best performance of the paint, ensure proper washing and cleaning of all algal and fungal growth, if any, at regular intervals of six months.

TECHNICAL DETAILS

- a. Drying time:** Surface dry time 2.5 hours
- b. Sheen levels:** 15-35 at 60 deg GH
- c. Flash point IS101/1987 Part 1 Sec 6:** 35°C (95°F)
- d. Stability of thinned paint:** To be used within 24 hours

PRECAUTIONS

- Do not apply when ambient temperature is less than 10°C or if the temperature might drop to this level within 4 hours of application.
- Do not over-thin or over-extend the brush.
- Tint using Asian Paints machine colourants only
- Stir well and strain before use.
- Tinted paints need thorough shaking immediately after tinter addition as well as before use.

SAFETY FEATURES

- Kindly refer to the MSDS for Asian Paints Premium Apcolite Satin Enamel which gives detailed information on safety measures while handling the paint, which is available on request.
- Store the container with the lid tightly closed in an upright position, in a cool, dry place.
- Keep out of reach of children and away from eatables.
- May be harmful if swallowed. In case of ingestion seek immediate medical attention.
- Wear eye protection during application. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- In case of skin contact immediately wash skin with soap and plenty of water. Get medical attention if irritation develops or persists.
- Do not breathe vapour or spray. It is recommended to wear suitable nose pad during sanding and surface preparation to avoid dust inhalation
- Do not pour leftover paint down the drain or in water courses.
- In the event of spills, contain spillage using sand or earth.
- No added Lead, Mercury or Chromium compounds.

#Please refer to the warranty documents for the product at the Asian Paints Website for further information.