

PRODUCT CODE 1073, 1075, 1077, 1082, 1083, 1084, 4158, 4159, 4160

WoodTech Emporio PU Black

Asian Paints WoodTech Emporio PU Black is an acrylic based opaque coating, which offers excellent stain resistance, better hardness and long-lasting durability.

PRODUCT BENEFITS

Quick Drying

Complete your painting in half time as required for a regular PU.

Protection

WoodTech Emporio PU has the best scratch, stain and heat resistance in the PU finishes category.

Clarity of Image

WoodTech Emporio PU has high clarity of image, leading to a reflection similar to that seen in a mirror.

Hardness

WoodTech Emporio PU has the highest film hardness, making this product very durable.



PRODUCT FEATURES

DURABILITY



BEST IN CLASS


✓ HIGH

MEDIUM

LOW

COLOURS AVAILABLE

Black*



AVAILABLE PACKS



Emporio PU Black Sealer (1082) - 4 ltrs. and 20 ltrs.
Hardener - Emporio PU Black Sealer (1073) - 2 ltrs. and 10 ltrs.
Emporio PU Black Matt (1083) - 4 ltrs. and 20 ltrs.
Hardener - Emporio PU Black Matt (1075) - 2 ltrs. and 10 ltrs.
Emporio PU Black Glossy (1084) - 4 ltrs. and 20 ltrs.
Hardener - Emporio PU Black Glossy (1077) - 2 ltrs. and 10 ltrs.
Emporio PU Black Sealer Kit (4158) - 1 ltr.
Emporio PU Black Matt Kit (4159) - 1 ltr.
Emporio PU Black Glossy Kit (4160) - 1 ltr.

COVERAGE

On smooth sanded wooden surface by Spraying



1 COAT

8 - 10 sq.mtr/Ltr/Coat**

**Actual coverage may vary from the quoted coverage due to factors such as method and condition of application and surface roughness and porosity.

FINISH

↓ MATT SOFT SHEEN RICH SHEEN ↓ HIGH GLOSS

HOW TO APPLY

PRE PAINTING STEPS



CLEANING: Ensure wood to be coated is properly seasoned and all impurities are removed from the wood. Check and maintain moisture level in wood in the range of 10- 15%. Avoid higher moisture content in wood as it will lead to surface defects like popping, pinholes, and poor substrate wetting. Application area & surface must be free from dust, oil, grease, or foreign particles to prevent contamination. Compressor must be free from moisture and oil. Ensure good ventilation in application area.



SANDING: Sand the wooden surface along the grains using sand paper no.180, and then 320 or 400. Wipe surface to clean off loose dust particles.



INSULATING: (Recommended) Apply 1-2 coats of WoodTech Epoxy Insulator to insulate from oil & resin from the wood, also it reduces absorption of a paint material on Plywood & MDF.



DENT FILLING: If the surface has dents, apply WoodTech Filler with a putty knife over the dented area.

NOTE: (1.) WoodTech Emporio PU base should be thoroughly stirred and mixed with WoodTech Emporio PU hardener and thinner in the specified mixing ratio. (2.) WoodTech Emporio PU Opaque must not be polluted with oil, varnish or the like and must not be sanded with steel wool between coats. (3.) Base and hardener of 2 pack system must be consumed within one week of opening the fresh containers. The containers should

PAINT APPLICATION PROCESS

APPLICATION	CODE	THINNER	DILUTION %	APPLICATION VISCOSITY (SEC)	RECOATING PERIOD
STEP 1 WOODTECH EMPORIO PU BLACK SEALER FIRST COAT SPRAY	1082+1073 / 4158 IN 2:1	PU THINNER (1532/5442)	SPRAY 15 - 30	SPRAY 14 - 17	3 - 4 HRS (SHOULD NOT EXCEED 72 HRS)
STEP 2 SANDING	SAND THE SURFACE WITH EMERY PAPER 320 OR 400 AND WIPE CLEAN				
STEP 3 WOODTECH EMPORIO PU BLACK SEALER SECOND COAT SPRAY	1082+1073 / 4158 IN 2:1	PU THINNER (1532/5442)	SPRAY 15 - 30	SPRAY 14 - 17	3 - 4 HRS (SHOULD NOT EXCEED 72 HRS)
STEP 4 SANDING	SAND WITH SAND PAPER NO. 320 OR 400 AND WIPE CLEAN (APPLY THIRD COAT IF REQUIRED BEFORE TOP COAT APPLICATION, SAND WITH SAND PAPER NO. 320/400 AND WIPE CLEAN)				
STEP 5 WOODTECH EMPORIO PU BLACK MATT / GLOSSY FIRST COAT	1083+1075 IN 2:1 (MATT) OR 1084+1077 IN 1:1 (GLOSSY) 4159 OR 4160	PU THINNER (1532/5442)	SPRAY 15-30 (MATT) / 10-20 (GLOSSY)	SPRAY 14 - 17	3 - 4 HRS (SHOULD NOT EXCEED 72 HRS)
STEP 6 SANDING	SAND THE SURFACE WITH EMERY PAPER 320 OR 400 AND WIPE CLEAN				
STEP 7 WOODTECH EMPORIO PU BLACK MATT / GLOSSY SECOND COAT	1083+1075 IN 2:1 (MATT) OR 1084+1077 IN 1:1 (GLOSSY) 4159 OR 4160	PU THINNER (1532/5442)	SPRAY 15-30 (MATT) / 10-20 (GLOSSY)	SPRAY 14 - 17	3 - 4 HRS (SHOULD NOT EXCEED 72 HRS)
(APPLY THIRD COAT IF REQUIRED AFTER SANDING WITH SAND PAPER NO. 320/400 AND WIPE CLEAN)					

be tightly closed after use to avoid any moisture contamination with the liquid material.(4.) WoodTech Emporio PU Black should be thoroughly stirred and mixed with the hardener and thinner in the specified mixing ratio. (5.) If the coating gets physically damaged (cuts and dents) due to impact of sharp objects or any other means, after application or in normal usage, then the damaged surface must be repaired by application of fresh coats

of WoodTech Emporio PU Clear on the specific area. (6.) Recoat period is quoted for 30°C and 75% relative humidity, these may vary under different conditions. (7.) Spraying air pressure 2.2 to 2.8 Kgs/sq.cm. (8.) Viscosity as measured through a Ford cup B4 at 30°C.

ADDITIONAL INFORMATION

POST PAINTING CARE

For removing stains on tiles and metal surfaces, apply A1/A1 Gold Thinner/NC Thinner on the surface and wipe clean. If stains are difficult to remove, scrapping can be done after applying A1/A1 Gold Thinner/NC Thinner on the stained area. Precautions need to be taken while spraying / brushing, like masking of adjoining areas with suitable material, as the stains may be difficult to remove if present on wood or coated wooden and wall surfaces.

TECHNICAL DETAILS

a. Dry to touch time: Surface dry time approximately 40 minutes Tack Free time 3 hrs

b. Gloss levels: 95% minimum (Glossy) on coated Wooden Panel at 60 Gloss Head and 18 - 23 % (Matt) on coated Wooden Panel at 60 Gloss Head.

c. Flash point IS101/1987 Part 1, Sec 6: Above [Matt {1074} - 9°C (15.8 F) Glossy {1076} 23°C (73.4F)

d. Stability of thinned paint: To be used within 3 hours

e. Shelf Life: 36 months for base and 24 months for hardener and 18 months for kits from date of manufacture in original tightly closed container away from direct sunlight and extensive heat.

PRECAUTIONS

- For optimum performance, Asian Paints Woodtech Emporio PU Black must be applied at a temperature between 20°C and 40°C and humidity not above 75%.
- Do not over-thin and mix according to recommended ratios
- Stir well and strain before use.
- For best performance, choose appropriate % of the thinner as per the climatic conditions. Choose slow drying thinner for application at higher temperature.

SAFETY FEATURES

- Kindly refer to the MSDS for Asian Paints WoodTech Emporio PU Black, which gives detailed information on safety measures while handling the paint.
- Store the product at ambient conditions in well ventilated locations and away from source of ignition and fire.
- Use protective equipment like rubber/polyurethane gloves, safety goggles/glasses, face mask while handling the paint.
- Avoid eye and skin contact. In both cases wash with soap and plenty of water. Get medical attention if irritation develops or persists.
- Do not inhale or ingest. In case of inhalation move to fresh air and seek medical attention if symptoms persist in both cases.
- No added Lead, Mercury or Chromium compounds.
- Left-Over Paint Disposal: Left-over paint/drums should not be disposed in soil/drains.
- Consumers should consult a local recycling agency for proper disposal of paint/drums.